

### Facestock

Extrusion coated three layer laminate (C1S paper 50gsm / LDPE 12 / 6,5µ Alu foil / 25g PE)

Basis Weight	105 g/m <sup>2</sup>	ASTM D646
Caliper	85 µm	ISO 534
Burst	Max 0.5 KPa	ASTM D774
Elongation CD	MIN 3.0 %	ASTM D828
Elongation MD	MIN 1.5 %	ASTM D828
Heat Seal front	150-180 °C	
Moisture vapor transmission rate	Max 0.5 g/sqm/24h	Astm F 1249 (38°C; 90%RH)
Oxygen Permeability	Max 0.5 cm <sup>3</sup> /m <sup>2</sup> /24 hr	ASTM D3985
Tensile strength MD	Min 5.5 daN/15 mm	ASTM D828
Tensile strength CD	Min 2.5 daN/15 mm	ASTM D828
Tear Strength MD	MIN 350 mN	ISO 1974
Tear Strength CD	MIN 400 mN	ISO 1974

### Shelf Life

To obtain optimal performance, use this product within one year of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

## AN048

## Fasson ®

## PAPER WEB50



PAPER WEB50

*This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.*

*If you would like to make a suggestion or comment on this datasheet, please send an email to [datasheet.mgmt@eu.averydennison.com](mailto:datasheet.mgmt@eu.averydennison.com)*

### Avery Dennison Materials Group Europe

Willem Einthovenstraat 11  
2342 BH Oegstgeest  
The Netherlands  
+31 (0)85 000 2000

#### Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>



©2023 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.