

Facestock

A bi-axially oriented, gloss clear polypropylene film with a print-receptive top-coat.

Basis Weight	84 g/m ²	ISO 536
Caliper	91 µm	ISO 534

Adhesive

R1490M is a removable solvent adhesive

Liner

BG40WH FSC, a supercalandered siliconized white glassine paper.

The liner is made from FSC® certified paper (FSC Mix Credit, chain-of-custody number: CU-COC-807907, Licence Code: FSC-C004451).

Basis Weight	57 g/m ²	ISO 536
Caliper	51 µm	ISO 534

Laminate

Total Caliper	157 µm±10%	ISO 534
---------------	------------	---------

Performance Data

Initial Tack	7 N/25mm	FTM 9 glass
Peel Adhesion 90°	3 N/25mm	FTM 2 st.st.; 24 hrs.

Min. Application Temp.	+5 °C
Service Temperature	-20 °C to +80 °C

Applications and Use

Applications are predominantly in market segments where rigid containers are used (e.g. Glass, PET). Due to fairly rigid nature of the film care should be taken with use on non-uniform surfaces and where a very high level of squeezability is desired.

R1490M is a removable solvent adhesive exhibiting excellent UV resistance, clean removability and a smooth peel from PE and PP substrates. The adhesive shows moisture and solvent resistance meeting the requirements of personal care, cosmetics & baby wet wipes.

Conversion and Printing

The modified acrylic based topcoating allows printing by the usual printing technologies including letterpress, flexo, gravure and screen printing, giving good results with solvent, UV curing and water based inks. Good acceptance of hot foil blocking. Conversion with flatbed and solid/magnetic rotary dies is very good. Square corners should be avoided.

Compliance and Approvals

The adhesive R1490M is suitable for contact with dry, moist, and non-fatty foodstuffs in this construction. For complete information regarding the food contact compliance status, please contact your local sales representative for a Food Contact Statement.


Shelf Life

To obtain optimal performance, use this product within two years of the date of manufacture, under storage conditions as defined by FINAT (20-25°C; 40-50%RH). Prolonged storage outside these conditions might reduce the shelf life.

AU331

Fasson®

PP90 TOP CLEAR R1490M-BG40WH IMP FSC



PP90 TOP CLEAR

R1490M

BG40WH FSC



The mark of
responsible forestry

This is an automatically generated datasheet. All data to be considered as typical values and subject to change without prior notice. Further testing is always recommended.

If you would like to make a suggestion or comment on this datasheet, please send an email to datasheet.mgmt@eu.averydennison.com

Avery Dennison Materials Group Europe

Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands
+31 (0)85 000 2000



Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>

©2025 Avery Dennison Corporation. All rights reserved. Avery Dennison and all other Avery Dennison brands, this publication, its content, product names and codes are owned by Avery Dennison Corporation. All other brands and product names are trademarks of their respective owners. This publication must not be used, copied or reproduced in whole or in part for any purposes other than marketing by Avery Dennison.